

# NAB/800/Z



VUDAC IMPREGNANTS

## Characteristic

NAB/800/Z is a medium-viscosity single-component impregnant based on unsaturated polyester-imide resin dissolved in reactive diacrylate. It has a clear amber look and is odorless. There is little emission (VOC) released during curing. Does not pollute the work environment, does not create a fire hazard. Waste air does not need to be cleaned.

Impregnation is characterized by the following properties:

- ecological
- excellent thermal resistance
- excellent mechanical strength
- the cleanliness of the systems surface after impregnation
- short curing time
- minimum losses during curing
- exceptional cure efficiency
- customizable processing properties according to customer requirements

## Field of application

NAB/800/Z is suitable for trickling applications in temperature class H. It is designed for the impregnation of thermally stressed windings of alternators, electric high speed rotary machines of domestic tools and power tools.

## Processing

Impregnant is developed for trickling impregnation by closed impregnation lines under atmospheric pressure. Sufficient suction of the vapors produced during curing must be ensured. Exact instructions for processing will be provided depending on the customer's processing method

Since it is a one-component system, additional additives are not required before use. To achieve the maximum lifetime of the impregnant, its recommended to maintain operating temperature 25°C as maximum.

**It is highly recommended to keep the temperature of dosing nozzle under the 40 °C when impregnation line is paused. Due to high reactivity of impregnant higher temperatures may cause obstruction of the nozzle.**

When handling the impregnating resin, follow the safety instructions in the Safety Data Sheet.

To clean the equipment and work tools from undamaged impregnant it is recommended to use VUKI thinner T5.

## Hardening

Curing conditions:

- Conventional curing:
  - preheating: 105 – 110 °C for 20 – 45 min
  - curing: 30 min from reaching 120 °C in the winding  
15 min from reaching 130 °C in the winding
- Oven has to be equipped with vapor extraction



# NAB/800/Z



VUDAC IMPREGNANTS

## Processing properties

Parameter	Standard	Condition	Value	Unit	Description
Density	STN EN ISO 2811-1	20 °C	1050 – 1150	kg/m <sup>3</sup>	
Viscosity	STN 67 3014	25 °C	700 – 1000	mPa.s	value adjustable according to customer request
Flash point	STN EN ISO 2592		> 112	°C	
Gel time	DIN 16 945	100 °C	2 – 5	min	
Reaction time	STN EN 60455-2	100 °C	2 – 6	min	
Exothermic temperature	STN EN 60455-2	100 °C	180 – 230	°C	
VOC			< 1,5	%	
Hardening time		120 °C	30	min	
		130 °C	15	min	
Effect on enameled wires	STN EN 60851-4,5 STN EN 60317		suitable		compatible with all commonly used wires

## Parameters after hardening

Parameter	Standard	Condition	Value	Unit	Description
Layer thickness on AL sheet			10 – 15	µm	
Water absorption	STN EN ISO 62	168 h at 23 °C	< 0,6	%	
Electrical strength	STN EN 60243-1	23 °C 180 °C after 96 h/ 92% r.h./ 23 °C	60 50 50	kV/mm	cylindrical electrodes ø 6 mm
Volume resistivity	STN EN 62631-3-1	23 °C 180 °C after 168 h in water, 23 °C	10 <sup>14</sup> 10 <sup>9</sup> 10 <sup>14</sup>	Ω.m	
Twisted coil strength	STN EN 61 033 art. 2.1 method A	23 °C	200	N	
Helical coil strength	STN EN 61 033 art. 2.1 method B	23 °C	120	N	
Temperature index	STN IEC 60 216		180	°C	





### Packing, storing and manipulation

Impregnating resin is supplied in non-returnable, clean, metal drums with weight 25 kg and 200kg. Alternatively, other packaging can be used according agreement. Impregnating resin is stored in tightly closed containers in a dry, ventilated place at + 5 ° C to + 25 ° C. When the storage conditions are met, the quality of the impregnating resin is guaranteed 4 months from the date of manufacture.

**CAUTION:** Extreme heat or contamination may result in the polymerization and deterioration of the impregnant!

Impregnating resin is not classified as a dangerous product.

### Certificates

- twisted pairs: 180 °C, thermal class H (UL file E233982)
- helical coils: 180 °C, thermal class H (UL file E233982)

### NOTE

The information in this document is consistent with our best knowledge of the date of publication. This information can be a subject of revision without prior notice if new knowledge and experience are available. The data provided falls within the normal range of product properties and relates only to the specified material. These data may not apply to materials used in combination with other materials or ingredients or other processes, unless expressly stated otherwise. The data provided should not be used to set limits or used separately as a basis for the sample: they are not intended to compensate for any testing that may be necessary to make a decision as to whether the specific material is suitable for your particular purpose. Because VUKI cannot predict all variants of end-use product conditions, VUKI does not provide guarantees and has no responsibility with respect to any use of this information. Nothing in this publication is considered to be a use or recommendation to violate any patent rights.

### Contact

VUKI a.s., Rybníčná 38, 831 07 Bratislava 06  
Customer service – tel.: +421 906 063 231, +421 906 063 107  
e-mail: [info@vuki.sk](mailto:info@vuki.sk)  
<http://www.vuki.sk>

### Version

2023-03-01